

СООБЩЕНИЯ  
ОБЪЕДИНЕННОГО  
ИНСТИТУТА  
ЯДЕРНЫХ  
ИССЛЕДОВАНИЙ

Дубна

98-267

E17-98-267

A.L.Kuzemsky<sup>1</sup>, I.G.Kuzemskaya<sup>2</sup>, A.A.Cheglov

ROLE OF LAYERED STRUCTURE  
FOR SUPERCONDUCTING CRITICAL  
TEMPERATURE OF THE MERCUROCPRATES

---

<sup>1</sup>E-mail: kuzemsky@thsun1.jinr.ru

<sup>2</sup>High Pressure Physics Institute, Russian Academy of Sciences, 142092  
Troitsk, Moscow Region, Russia


# 1 Introduction

There is considerable current interest in the properties of superconducting copper oxides. The studies of the mercurocuprate family of high-temperature superconductors (HTSC) has been the object of special interest during last years after their discovery [1], [2]. Particular importance is the question of interrelation of crystal structure and superstructure and superconductivity and the role of anisotropy in layered superconducting cuprates. Mercurocuprates have a pronounced layered structure and have raised once again the problem of how a structure of these materials affect their properties. It is well established that the  $CuO_2$  layers are responsible for the superconductivity in cuprates and that the electrical properties are governed by a charge carrier density of these layers. The homologous series  $HgBa_2Ca_{n-1}Cu_nO_{2n+2+\delta}$  is of special interest because it culminates the fascinating features of HTSC and are still most high-Tc representatives of cuprates [3],[4]. One of the most important issue for mercurocuprate family is to understand the exact role of layered structure and most important parameters that govern the highest value of transition temperature of these materials. Recently, there has been great progress in synthesis of high quality samples [5]- [8] and detailed structural studies [9]- [11]. The structure of the family of mercurocuprates can be viewed [12], [13] as consistent of  $Ca_{n-1}Cu_nO_{2n}$  block and the  $Hg-O_\delta$  block which play a role of reservoir of charge. The fabricating of homologous series  $HgBa_2Ca_{n-1}Cu_nO_{2n+2+\delta}$  has been performed using the high-pressure high-temperature synthesis which seems to be the efficient and workable method to produce high quality  $Hg$ -superconducting samples [5] - [8]. The synthesis of  $n = 1, 2, \dots, 8$  of the  $Hg$ -based homologous series was performed by this and other techniques with  $T_c = 97$  K for  $n = 1$ ,  $T_c = 127$  K for  $n = 2$ ,  $T_c = 135$  K for  $n = 3$ ,  $T_c = 126$  K for  $n = 4$ ,  $T_c = 110-114$  K for  $n = 5$ ,  $T_c = 96-100$  K for  $n = 6$  and  $T_c = 88$  K for  $n = 7$  (see Table 1 ( c.f. [8])). The experimental results on the dependence of

Table 1

$n$	1	2	3	4	5	6	7
$T_c, K$	97-98	127	135	125-126	110-114	96-100	88
$\delta$	0.08	0.22	0.28-0.35	0.4(1)	0.32(2)	-	-
$a, A$	3.880	3.8580	3.852	3.847	3.8523(4)	3.8533	3.847-851

the critical temperature on the number of layers  $n$  presented on Fig.1. On the Fig.2 the dependence of the  $T_c$  on the lattice distance  $a$  for  $n = 1 - 5$  members of family is presented.



The highest superconducting transition temperature at ambient pressure was observed for the third ( $n = 3$ ) of *Hg*-based copper-mixed oxide series  $HgBa_2Ca_2Cu_3O_{8+\delta}$  (*Hg*-1223) with  $T_c$  (onset) at 135 K after which a saturation seemed to be reached (see Fig.1, Fig.3). This feature of the highest  $T_c$  for  $n = 3$  is analogous to that occurred in the *Tl*- and *Bi*-based series. Unfortunately, mercurocuprates have been produced, are as a rule, not in their optimum doping state. This requires some additional treatment to achieve their highest temperature. There are an important differences between the mercurocuprates and the thallium analogues. One of the main differences is that connected with the partially occupied oxygen sites in the region between  $CuO_2$  planes, occupancy for which in mercurocuprates is very small. Thus the doping state of mercurocuprates can be controlled by changing the excess oxygen content [14], [15]. It is also important to note that for the mercurocuprate family the unilayer, bilayer, trilayer etc. dependence of physical properties show a different behavior as regards to anisotropy (two- or three dimensional nature) [16], [17].

The concept of a homologous series [4], which in the case of mercurocuprates play an especially important role, raise the natural question about dependence of a superconducting critical temperature of this family of layered copper oxides from the number of pairs ( $n - 1$ ) of  $CuO_2$  and bare cation planes in the infinite layer block. In another words, because of one member of one homologous series has the same charge-reservoir block [4] but the number of  $CuO_2$  planes ( $n$ ) is different, the main interest is dependence  $T_c(n)$  [18], [19].

There seems to be a close relationship between the average copper valence and the phase produced in the high-pressure synthesis of mercurocuprates [2]. This is related with the oxidation of the  $CuO_2$  layers. According to Ref. [2] the formal copper valence for different members of mercurocuprate family is equal to  $\nu_{Cu} = 2(n + \delta)/n$ . The averaged copper valence  $\langle \nu_{Cu} \rangle$  is the tunable parameter [20] that characterizes the synthesis of different phases and favour the low member of the family for high copper valences while high members are only obtained with low average copper valence. The values of  $\delta$  obtained from neutron scattering experiments lead to conclusion that the extra oxygen content, and consequently the copper valence and lattice parameter depend on the number of  $CuO_2$ -layers (Fig.3) and on heat treatment of the samples.

The  $T_c(n = 1, 2)$  can be changed by reducing or oxidizing treatments, contrary to the  $T_c(n = 3)$  which is not so strongly influenced by high pressure oxygen treatment. This may reflect the important fact that in *Hg* - 1223 structure, the distribution of charges between the two type of  $CuO_2$ -layers seems to be different. Such a structural specific feature which include the interplay of two "active" elements of different kind could be responsible for this behaviour. In the simplest case it could be the planes and the chains but as

regards to the inequivalent  $CuO_2$  layers in multilayer structure the inner and outer  $CuO_2$  layers can have different charge carrier density. Thus the correlation between the copper valence, lattice parameters and extra oxygen contents becomes then important (Fig.4). These circumstances should be keeping in mind when discussing the number of layer dependence of  $T_c(n)$  [13].

In the present paper we will analyse the physics of the optimally doped layered mercurocuprate family from the structural point of view. The superconducting transition temperature dependence from the number  $n$  of  $CuO_2$  planes in copper oxides will be described in the framework of workable phenomenological model and compared with experimental data.

## 2 Layered superconductors models

The problem of theoretical calculating of the superconducting critical temperature of layered superconductors in the context of copper oxides has been investigated previously to explain the variation of  $T_c$  with the number  $n$  of adjacent  $CuO_2$  planes, present in the various superconducting copper oxide compounds. The approach based on a two dimensional model for electronic structure of a  $CuO_2$  sheet has been proposed very early in Refs. [21], [22]. It was related with the statement that a 2D electronic band always shows a logarithmic singularity in the density of states. For  $n$  sheets, the density of states in two dimensions was proposed to be  $N = nN_0$  and the effective electron-phonon interaction  $\lambda = n\lambda_0$ . The law  $T_c(n) = T_0 \exp -1/\sqrt{n\lambda_0}$  has been derived. This formula even for a such oversimplified model was valid only for small  $n$ 's. An another mean-field approach was proposed in Ref. [23], where it was insisted that the average spacing between the  $CuO_2$  layers and not merely the number of layers per unit cell determine the critical temperature. A more sophisticated and detailed theory was proposed in Ref. [24] which give the monotonic increase of  $T_c(n)$  and upper limit for mercurocuprate family  $T_c(n = \infty) = 153$  K. Very recently the interlayer effects in *Hg*-based cuprates under high pressure for samples with  $n = 1 - 6$  sublayers in the unit cell was considered in Ref. [25]. The theory of the interlayer tunneling of holon pairs has been used and applied for  $n > 4$  cases and agreement and disagreement with experimental results was analyzed. D.T.Jover et al [26] have considered the mercurocuprates up to  $n = 4$  on the basis of the model approach of charge redistribution of holes among the various  $CuO_2$  layers [27]. They found out that for  $n \geq 3$  this distribution is highly nonhomogeneous. This can lead to observable nonmonotonic  $n$  dependence of  $T_c(n)$  as was discussed in details in Ref. [25].

As already mentioned, the different members of the mercurocuprate family

are found to exhibit different optimal superconducting transition temperatures which increase up to the third member, after  $T_c$  decreases. According to Ref. [2] an important and general structural feature of the mercurocuprates is that the apical  $Cu-O$  distances are larger than the corresponding distances in the other cuprates and the  $Cu$  and  $O$  atoms forming the  $CuO_2$ -layers are coplanar. These structural features could be responsible for the highest transition temperature, however a satisfactory overall picture of the nature of this high- $T_c$  behaviour is still in the process of evolution. Unfortunately, we have, at the present time, no generally accepted and complete formal theory of HTSC. The essence of the problem is in the inherent interaction (and coexistence) between charge and spin degrees of freedom which are coupled in a very nontrivial self-consistent way [28]. Since the honest theoretical treatment of the all above mentioned problems is very complicated, perhaps, it is instructive to look again at the physics involved from a phenomenological point of view.

### 3 Phenomenological Models

The phenomenological approach to layered copper oxides was developed by many authors. The consideration of inequivalent layers in the phenomenology of cuprates was done in Ref. [29] in terms of proximity effect [30] between the superconducting and insulating layers forming the unit cell of various copper oxides. The model accounted for observed positive curvature in the temperature dependence of the  $H_{c2}^1$  and do not tackled the calculation of transition temperature. Subsequently, different authors have used several distinct approaches to realize this idea of inequivalent layers. It is interesting to note that notion of distinct "active" elements in the structure (type of plane, or chain) in layered cuprates was formulated in the very beginning stage of the studies of these materials even with some exotic model statements that adjacent  $Cu-O$  layers have negative Josephson coupling [31], forcing the order parameter to change sign from one layer to the next. The phenomenological approach for calculation of transition temperature of layered cuprates has been proposed in Ref. [32]. The physical idea was that there are distinct "active" elements in the multilayer structure. To each active element denoted  $l$  in the structure is associated a Ginsburg-Landau (GL) order-parameter field  $\psi_l(r)$ . Each of these  $\psi_l(r)$  has some distinct "bare" transition temperature  $T_l^0$  in that structure. The full GL theory is a generalization to coupling order parameters of the seminal work of Lawrence and Doniach (LD) [33]. The LD theory is valid for disturbances in which  $\psi_l$  varies slowly on the scale of  $s$  and close to  $T_c$ . The approach of Ref. [32] have demonstrated that for polytype multilayer copper oxide systems it is possible to obtain the increasing  $T_c(n)$ , where  $n$  is

polytype number  $n = 2, 3, \dots, \infty$ , with upper limits for  $T_c$ . In this paper we apply this line of reasoning (with suitable modifications) for the mercurocuprate family.

In order to model the layered structure of the mercurocuprates, we use the LD model, which consists of superconducting sheets separated by a distance  $s$ , with a Josephson coupling between the sheets. The GL functional is

$$F = \sum_l \int d^2x \left( \frac{\hbar^2}{2m} \left| \left( \nabla_l - i \frac{2e}{\hbar c} \vec{A}_l \right) \psi_l \right|^2 + \frac{\hbar^2}{2Ms^2} |\psi_l - \psi_{l+1}|^2 + a_l |\psi_l|^2 + \frac{1}{2} b_l |\psi_l|^4 \right) \quad (1)$$

where  $m$  and  $M$  are the effective masses in the  $a-b$  plane and along the  $c$  axis, respectively,  $a_l = a_l^0(T/T_l^0 - 1)$ . The simplified version of GL theory consider the competing order-parameter fields as spatially homogeneous and the temperature region just near the critical temperature. In the normal state,  $T > T_c$  all order parameters are zero. For  $T < T_c$  some order parameters  $\psi_l \neq 0$  for minimum free energy. Near  $T_c$ , if the coherence length perpendicular to the layers extends over many layers then the system acts as a bulk anisotropic superconductor.

The free energy density was taken in Ref. [32] as a bilinear form in the spatially independent order parameters

$$f = \sum_i a_i(T) |\psi_i|^2 + \sum_{ij} v_{ij} |\psi_i - \psi_j|^2 \quad (2)$$

here  $v_{ij}$  is the coupling coefficient. This lead to relevant secular equation of the form

$$\| (a_i(T) + n v_{ij}) \delta_{ij} - v_{ij} \| = 0 \quad (3)$$

According to Ref. [32], the transition temperature for an  $n$ -layer sample is determined as the maximum eigenvalue of the  $n$ -dimensional Jacobi (tridiagonal) matrix. It is possible to consider a system composed of  $n$  identical layers, where all parameters are identical ( $T_l^0 = T^0$  and  $v_{ij} = v$ ). For this case the explicit expression [32] for  $T_c$  provides that the largest solution is  $T = T^0$  and  $T_c(n)$  is an increasing function of  $n$  with upper limit  $T_c(n = \infty) = 141$  K. In the structural model we adopt in the present paper a periodic layered system, whose unit cell contains two kinds ( $a$  and  $b$ ) of layers ("active" elements) are considered. The first and  $n$ -th layers of type  $a$  have the same order parameter ( $1 \leq a \leq n$  and  $1 \leq b \leq m$ ). Thus we can incorporate in our formulation the presence of two type of layers. The equation (3) is identical to the following expression

$$F_{ij} = \left( T_i^0 - \frac{v_{i-1,i}}{a_i^0} - \frac{v_{i,i+1}}{a_i^0} \right) \delta_{ij} + \frac{v_{ij}}{a_i^0} \delta_{i,j\pm 1} \quad \det(TI - F) = 0; \quad (4)$$



Equations (3) and (4) properly determine the critical temperature as a maximum solution  $T_i^{max}$  of this periodic  $n - m$  layered system. The numerical solution of these equations with reasonable parameters show that  $T_c$  of the whole system is raised with the number  $n$  and reduced with the number  $m$ . This reflect the fact that the amplitudes of the order parameters for  $a$ -layers are larger than those for  $b$ -layers. This interplay of the two order parameters of the two kind of active elements is one of the most important properties of the present phenomenological considerations.

Nevertheless, the model properties related to these effects do not give the observable "bell"-shaped form of  $T_c(n)$ . It is therefore of considerable interest to take into account the interlayer effects of charge redistribution to fit the experimental data.

## 4 The Charge Redistribution

The charge carriers in active  $CuO_2$  planes are the fundamental degrees of freedom which are primarily responsible for the essential physics. The problem how doping will modify the charge and spin distribution of the system is not well understood for HTSC [28]. Contrary to the insulating behaviour the doped systems still are not completely understood and create a number of controversy [27], [34]. This confirm the statement that the question about true nature of carriers in the copper oxides are one of the central in the field and are still open. It was emphasized in Ref. [34] that the distribution of charge among the  $CuO_2$  layers should be understood in order to describe adequately the variation of  $T_c$  with the number of  $CuO_2$  layer per unit cell in layered cuprates with three or more  $CuO_2$  planes.

The carrier concentration  $n_h$  is an crucial factor determining the critical temperature  $T_c(n_h)$  [25], [26]. It was supposed that in HTSC a charge redistribution may occur between the reservoir block and active block under various conditions like applied high pressure or with changing of composition, such as oxygen stoichiometry. In the multilayer structures there are a possibility of charge redistributing between the layers within a unit cell thus leading to models of "inequivalent"  $CuO_2$  layers. The inequivalent layer models reveal essential physics arising from the sensitivity to the transition of one of the subsystems to the superconducting state so that  $n_h$  should rearrange when the system becomes superconducting. In the considered here the case of the mercurocuprate family with  $n \geq 3$  are the holes in inner and outer  $CuO_2$  planes for which charge redistribution transfer with the "reservoir" block seemed could be different.

In addition, it was pointed out [35] that the electromagnetic response of the

layered superconductors can have a peculiar behavior related to the specific of the interlayer charge transfer. One of the most important properties of the cuprate superconductors is that the frequency of the plasma with  $c$ -axis polarization is very low. An detailed analysis of the mercurocuprates in this respect will clarify the behavior of dielectric function and interlayer charge transfer in this family (c.f. [36]).

In our present work, ignoring at the first stage the subtleties of the delicate problem of the exact charge redistribution we adopt the following workable ansatz for the critical temperature  $T_a$  of an  $a$ -layer dependence on the number density of carriers of the form

$$T_a(x_c) = T_{a^0} \left( 1 - \left[ \frac{x_c - h_2}{h_1} \right]^2 \right)^{1/2} \quad (5)$$

where the carrier-number density  $x_c$  in a single layer is given by  $x_c = x_{out}^b [cm + 2(1 - c)] / (n + m)$  and  $x_{out}^b$  is the fraction of carriers which is provided by the outer  $b$ -layer adjacent to an  $a$ -layer per area while  $x_{in}^b = cx_{out}^b$  ( $c \leq 1$ ) is the corresponding quantity provided by an inner  $b$ -layer. Here  $h_1$  and  $h_2$  are fitting parameters. To proceed further we use the following model estimations :

$$T_b = \begin{cases} T_b^0 \left( \frac{x_c}{x_0} \right), & 0 \leq x_c \leq x_0; \\ T_b^0, & x_c \geq x_0; \end{cases} \quad a_b(x_c) = \begin{cases} a_b^0 T_b^0 \left( \frac{x_c}{x_0} \right)^{1/2}, & 0 \leq x_c \leq x_0; \\ 2a_b^0 T_b^0 \frac{x_0}{x_c + x_0}, & x_c \geq x_0; \end{cases} \quad (6)$$

Here  $x_0 = m^* t_{\perp} / \pi \hbar^2$  and  $v = v_i$  have no  $x_c$  dependence (c.f. [33]).

With these simplifications it is possible now to calculate the critical temperature. There are the following free model parameters:

- (i)  $n$  and  $m$  which determine the structure;
- (ii)  $x_{out}^b$  and  $c$  which determine  $x_c$ ;
- (iii)  $x_0$  and  $T_b^0$  which determine  $T_b$ ;
- (iv)  $a_a^0$ ,  $a_b^0$  and  $v$ .

We have calculated  $T_c(n)$  with  $m$  fixed for  $m = 1, 2, 3, 4$ . The results of numerical calculations for  $T_c(n)$  for  $m = 3$  (Fig.5) are shown as a solid line. Thus, incorporating the charge interlayer redistribution, it is possible to restore the observable "bell"-shaped dependence even in the simplest version of the model and fit the experimental results well.

## 5 Conclusions

In summary, in this paper we have presented a simple phenomenological model which rationalizes reasonably the currently available experimental data for the mercurocuprate family. We discussed the main structural features of layered mercurocuprates and gave the physical interpretation and plausible arguments

on the role and significance of structural anisotropy and interlayer effects in this family. It was shown that within the LD-weak-link type model the observable behavior could not be explained without an additional invoking to the incorporating of the interlayer charge redistribution. Within the framework of the our combined model the experimentally observed nonmonotonic "bell"-shaped dependence  $T_c(n)$  was traced back to the experimental one with reasonable accuracy. Therefore, in spite of the rather crude nature of our phenomenological model approach, the results presented here show that our threatment is quantitatively applicable to the layered mercurocuprate family. From the another side, our analysis favours an approach which are describable in terms of the generalized LD model with suitable charge redistribution corrections. This conclusion should be further substantiated by considering the more general GL model for layered superconductors as well as the more sophisticated description of the charge redistribution. A detailed consideration of these questions as well as an extended version of our numerical calculations will be discussed elsewhere.

## 6 Acknowledgements

We indebted to E.S.Itskevitch, E.V.Antipov and A.M.Balagurov for stimulating discussions. I.G.K. was partially supported by Russian Scientific Program on Superconductivity (grant 96045).




Fig. 1: Dependence of the superconducting critical temperature on number of layers  $n$  from Ref. [19].




Fig. 2: Dependence of the superconducting critical temperature on lattice distance  $a$  for  $n = 1 - 5$ .  $\square$  -  $n = 1$ ;  $\bullet$  -  $n = 2$ ;  $\triangle$  -  $n = 3$ ;  $\diamond$  -  $n = 4$ ;  $\nabla$  -  $n = 5$ ; (c.f. [8])




Fig. 3: Dependence of the superconducting critical temperature and copper valence on number of layers  $n$  according to data from Table 1. Full line is the critical temperature and dashed line is valence.




Fig. 4: Lines of the equal values of  $T_c$  versus  $n$  and  $a$ .




Fig. 5: Dependence of superconducting critical temperature  $T_c(n)$  with  $m = 3$  fixed. Parameters:  $T_a^0 = 189.1$ ;  $T_b^0 = 88.1$ ;  $h_1 = 0.313$ ;  $h_2 = 0.504$ .

## References

- [1] S.N.Putilin et al., Nature 362 (1993) 226.
- [2] E.V.Antipov et al, Physica C235-240 (1994) 21
- [3] J.Akimitsu and M.Kokubun, in: *The Physics and Chemistry of Oxide Superconductors*, edited by Y.Iye and H.Yasuoka (Springer-Verlag, Berlin, 1992),p.17
- [4] H.Yamauchi, M.Karppinen and S.Tanaka, Physica C263 (1996) 146
- [5] I.G.Kuzemskaya et al, J.Low Temp.Phys. 105 (1996) 1565
- [6] I.G.Kuzemskaya et al, J.Superconductivity, 11 (1998) 117
- [7] K.A.Lokshin et al, Physica C279 (1997) 11
- [8] K.A.Lokshin et al, Physica C300 (1998) 71
- [9] E.V.Antipov et al, Physica C218 (1993) 348
- [10] V.L.Aksenov et al, Physica C275 (1997) 87
- [11] V.L.Aksenov et al, Phys.Rev. B55 (1997) 3966
- [12] M.Paranthaman and B.C.Chakoumakos, J.Sol.State Chem. 122 (1996) 221
- [13] A.Fukuoka et al, Phys.Rev. B55 (1997) 6612.
- [14] K.Fujinami et al, Phys.Rev. B56 (1997) 14790
- [15] A.M.Abakumov et al, Phys.Rev.Lett. 80 (1998) 385
- [16] Mun-Seog Kim et al, Physica C282-287 (1997) 1987
- [17] Mun-Seog Kim et al, Phys.Rev. B57 (1998) 6121
- [18] B.A.Scott et al, Physica C230 (1994) 239
- [19] J.Karpinski et al, J.Superconductivity 11 (1998) 119
- [20] M.Karppinen and H.Yamauchi, J.Superconductivity 11 (1998) 39
- [21] J.Labbe and J.Bok, Europhys.Lett. 3 (1987) 1225
- [22] J.Bok, Solid State Commun. 67 (1988) 251

- [23] D.Baeriswyl and T.Schneider, *Int.J.Modern Phys.B1* (1988) 523
- [24] K.Byczuk and J.Spalek, *Phys.Rev. B53* (1996) R518.
- [25] E.S.Itskevich and E.V.Zhasinas, *Physica C295* (1998) 193
- [26] D.Tristan Jover et al, *Phys.Rev. B54* (1996) 4265
- [27] M.Di Stasio et al, *Phys.Rev.Lett. 64* (1990) 2827
- [28] A.L.Kuzemsky, in: *Superconductivity and Strongly Correlated Electron Systems*, edited by C.Noce, A.Romano and G.Scarpetta (World Scientific, Singapoure, 1994), p.346
- [29] S.Theodorakis and Z.Tesanovic, *Phys.Lett. A132* (1988) 372
- [30] R.Yeh, *Ann.Phys. 46* (1968) 546
- [31] S.Theodorakis, *Phys.Lett. A132* (1988) 287
- [32] J.Birman and J.P.Lu, *Phys.Rev. B39* (1989) 2238
- [33] W.E.Lawrence and S.Doniach, in: *Proc. of the 12th Intern.Conf. on Low Temp.Phys. 1970*, edited by E.Kanda (Tokyo, 1971)p.361
- [34] E.M.Haines and J.L.Tallon, *Phys.Rev. B45* (1992) 3172
- [35] M.Tachiki et al, *Phys.Rev. B50* (1994) 7065
- [36] K.Kadowaki et al, *Physica C293* (1997) 130

Received by Publishing Department  
on September 28, 1998.

Куземский А.Л., Куземская И.Г., Чеглоков А.А.  
Роль слоистой структуры меркурокупратов  
для температуры сверхпроводящего перехода

E17-98-267

Изучалась физика высокотемпературных ртутных сверхпроводников с точки зрения особенностей их кристаллической структуры. Рассмотрение критической температуры перехода для семейства  $\text{HgBa}_2\text{Ca}_{n-1}\text{Cu}_n\text{O}_{2n+2+\delta}$  в зависимости от  $n$  проводилось в рамках феноменологического подхода. Зависимость  $T_c$  от  $a$ -параметра (и следовательно, от содержания кислорода  $\delta$ ) имеет универсальный колоколообразный характер. Подобный характер имеет также зависимость  $T_c(n)$  с максимумом при  $T_c(n=3)$ . Для объяснения этой зависимости использовалась феноменологическая модель слоистых сверхпроводников с учетом перераспределения заряда. Это позволило получить количественное согласие с наблюдаемой немонотонной колоколообразной зависимостью  $T_c(n)$ . Показано, что корреляция между параметрами решетки, валентностью, степенью окисления и числом слоев, по-видимому, имеет существенное значение для температуры сверхпроводящего перехода.

Работа выполнена в Лаборатории теоретической физики им. Н.Н.Боголюбова ОИЯИ.

Сообщение Объединенного института ядерных исследований. Дубна, 1998

Kuzemsky A.L., Kuzemskaya I.G., Cheglokov A.A.  
Role of Layered Structure for Superconducting Critical Temperature  
of the Mercurocuprates

E17-98-267

The physics of the mercurocuprate family was studied from the crystal structure point of view. A phenomenological approach determining the critical temperatures for homologous series  $\text{HgBa}_2\text{Ca}_{n-1}\text{Cu}_n\text{O}_{2n+2+\delta}$  depending of number of layers  $n$  was developed. Dependence of  $T_c$  vs.  $a$ -parameter (and consequently, oxygen content  $\delta$ ) have an universal «bell»-shaped character. The similar «bell»-shaped character has a number of layers dependence of  $T_c(n)$  with the maximum at  $T_c(n=3)$ . We have analysed dependence of a superconducting critical temperature of mercurocuprates and of the formal copper valence for different members of mercurocuprate family in terms of a phenomenological model of layered superconductors. The redistribution of charge was taken into account. This lead to observable nonmonotonic «bell»-shaped dependence of  $T_c(n)$  and provides a quantitative explanation of the experiments. It was shown that the correlations between the copper valence, lattice parameters and extra oxygen contents are the essential factors in the physical behaviour and HTSC characterization of the mercurocuprates.

The investigation has been performed at the Bogoliubov Laboratory of Theoretical Physics, JINR.

Communication of the Joint Institute for Nuclear Research. Dubna, 1998